



# GRAFITACK TRANSLUCENT SERIES

## REFERENCES TL128 to TL901

Released on 20th March 2009



### Description

The Grafitack Translucent series is a soft cadmium-free polymeric calendered translucent PVC film, provided with a pressure-sensitive permanent acrylic adhesive. This adhesive is protected by a high-quality silicone paper. A good recognizability is guaranteed by the red print on the material's backing paper. The TL colours all come with a backing paper with a grid printed underneath the silicone layer, to facilitate the re-positioning of characters.

### Composition

- Film : 80 micron thick polymeric calendered translucent PVC film
- Adhesive : permanent pressure-sensitive solvent-based acrylic adhesive, with a high resistance against UV-radiation, chemical products and humidity.
- Backing paper : siliconised white kraft paper of 120 gr/m<sup>2</sup>

### Application

The Grafitack Translucent series was developed for illuminated advertising, and can be used for numerous applications, such as on light boxes and also on most flexible sign faces.

### Product advantages

The high UV-resistance of the film guarantees nice longlasting illuminated advertising.

### Product specifications

Technical properties at a relative humidity of 50 ± 5 % and a temperature of 23 ± 2°C.

		Test method	Result
1.	<b>Thickness<sup>1</sup></b>		
	Thickness vinyl	Din53370	80 micron
	Thickness vinyl + glue + backing paper	Din53370	220 micron
2.	<b>Elongation at break<sup>2</sup></b>		
	In production-length direction	Din53455	> 130 %
	In cross direction	Din53455	> 150 %
3.	<b>Dimensional stability<sup>3</sup></b>	Finat 14	< 0.40 %
4.	<b>Degree of gloss</b>		
	Minimum (measuring angle 85°)	Din67530	25 %
	Maximum (measuring angle 85°)	Din67530	35 %
5.	<b>Adhesion strength<sup>4</sup></b>		
	After 20 minutes	Finat 1	15 N/25mm
	After 24 hours	Finat 1	18 N/25mm
6.	<b>Quickstick<sup>5</sup></b>	Finat 9	11 N
7.	<b>Expected outdoor life span<sup>6</sup></b>	-	7 years (colour 5-7 years) gold & silver 3 years
8.	<b>Temperature range</b>		
	At application	-	+10°C to +40°C
	At use	-	-20°C to +70°C
9.	<b>Colour back print</b>	-	red
10.	<b>Flammability</b>		
	If applied on aluminium, glass, steel = self-extinguishing		

## Storage instructions

All Grafitack materials always need to be stored in their original packing and with the original protection flanges (and preferably stored vertically).

In order to avoid any loss of quality, the Grafitack materials should also be stored in suitable conditions, that is at a temperature between 10 and 20°C, and a relative humidity of 50%.

Under these conditions, the Grafitack materials can be stored up to two years.

## Remarks

In order to achieve an optimal result, we advise you to clean the surface with isopropanol and/or to use a low-tack application tape !

## Important

The information, mentioned in this product data sheet, is based upon tests that were executed by Grafityp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is only given for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

- 1)** The thickness of the Grafitack materials may vary slightly. The indicated value is an average value, obtained from a series of measurements.
- 2)** The elongation at break of the Grafitack materials may vary slightly. The indicated value is a minimum value, obtained from a series of measurements.
- 3)** The dimensional stability is the shrinkage of the unprinted material in %. This value is measured by applying the film on aluminium, and placing it in a hot-air oven at 70°C for 48 hours (= Finat 14 Method, adjusted according to our own internally developed procedure). The indicated value is a maximum value, obtained from a series of measurements.
- 4)** The adhesion strength is measured on glass, and this after 20 minutes and after 24 hours. The film is removed again in an angle of 180° and at a speed of 300 mm/min. The indicated value is an average value, obtained from a series of measurements.
- 5)** The "Quickstick" is the direct adhesion strength, measured on glass. The indicated value is an average value, obtained from a series of measurements.
- 6)** The expected outdoor life span refers to outdoor use under Central European conditions and to vertical applications. The expected life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span. The life span can also differ, depending on the colour (due to the pigmentation).